

API Form 19B-Section 1

Conforms to All Requirements of Section 1

Special Test - See Remarks/Exceptions below

Service Company BashVzryvTechnologii, CJSC Explosive Weight 32,7 gm, RDX powder, Case Material Steel
 Gun OD & Trade Name 4,5" (114 mm) PKO114-AT Max Temp, °F 302(150°C) 2hr 284(140°C) 5hr 266(130°C) 12hr 248(120°C) 30hr 230(110°C) 72hr
 Charge Name ZPK114-AT-M-04 Maximum Pressure Rating 15011,4 (103,5 MPa) psi, Carrier Material Steel
 Manufacturer Charge Part No. 01 038 Date of Manufacture Sept. 10, 2015 Shot Density Tested 6,1 (20 shots/m) shots/ft
 Gun Type Expendable Gun TCP/Wireline Recommended Minimum ID for Running 5,748 (146 mm) in.
 Phasing Tested 60 degrees, Firing Order: Top Down X Bottom up Available Firing Mode: Selective X Simultaneous
 Debris Description N/A

Remarks/Exceptions per Section 1.12 Casing used: 6,61" (168 mm)x0,42"(10,6 mm) GRADE D, GOST 632-80; Gun shot with water

Casing Data 6,61" (168 mm) OD, Weight 27,65 (41,15 kg/m) lb/ft API Grade, Date of Section 1 Test October 12, 2015
 Target Data 149,61" (3800 mm) OD, Amount of Cement 27046,31 (12268 kg) lb, Amount of Sand 54026,48 (24506 kg) lb, Amount of Water 14255,09 (6466 kg) lb.
 Date of Compressive Strength Test October 12, 2015 Briquette Compressive Strength 6222,2 (42,90 MPa) psi, Age of Target 32 days

Shot No.	No 1	No 2	No 3	No 4	No 5	No 6	No 7	No 8	No 9	No 10	No 11
Clearance, in (mm).....	0,75 (19,1)	0,81 (20,7)	0,94 (24,0)	1,01 (25,7)	0,94 (24,0)	0,81 (20,7)	0,75 (19,1)	0,81 (20,7)	0,94 (24,0)	1,01 (25,7)	0,94 (24,0)
Casing Hole Diameter, Short Axis, in (mm)...	0,44 (11,2)	0,41 (10,4)	0,44 (11,1)	0,45 (11,4)	0,42 (10,7)	0,43 (10,9)	0,42 (10,7)	0,40 (10,2)	0,41 (10,3)	0,41 (10,4)	0,41 (10,5)
Casing Hole Diameter, Long Axis, in (mm)...	0,47 (11,9)	0,44 (11,1)	0,47 (11,9)	0,48 (12,1)	0,43 (11,0)	0,45 (11,5)	0,43 (11,0)	0,41 (10,3)	0,43 (11,0)	0,43 (11,0)	0,43 (10,9)
Average Casing Hole Diameter, in (mm).....	0,45 (11,55)	0,42 (10,75)	0,45 (11,50)	0,46 (11,75)	0,43 (10,85)	0,44 (11,20)	0,43 (10,85)	0,40 (10,25)	0,42 (10,65)	0,42 (10,70)	0,42 (10,70)
Total Depth, in (mm).....	LOST	67,7 (1720,6)	LOST	59,3 (1505,6)	64,7 (1642,6)	59,1 (1500,6)	60,1 (1525,6)	66,4 (1685,6)	LOST	LOST	LOST
Burr Height, in (mm).....	0,08 (2,0)	0,09 (2,2)	0,08 (2,0)	0,08 (2,1)	0,08 (2,1)	0,09 (2,2)	0,06 (1,6)	0,09 (2,2)	0,06 (1,5)	0,06 (1,6)	0,09 (2,2)

Shot No.	No 12	No 13	No 14	No 15	No 16	No 17	No 18	No 19	No 20	No 21	No 22	AVERAGE
Clearance, in (mm).....	0,81 (20,7)	0,75 (19,1)	0,81 (20,7)	0,94 (24,0)	1,01 (25,7)	0,94 (24,0)	0,81 (20,7)	0,75 (19,1)	0,81 (20,7)			xxxxx xxxxxx
Casing Hole Diameter, Short Axis, in (mm)...	0,41 (10,3)	0,43 (10,8)	0,40 (10,2)	0,41 (10,3)	0,40 (10,2)	0,41 (10,5)	0,40 (10,2)	0,43 (10,9)	0,40 (10,1)			0,42 (10,57)
Casing Hole Diameter, Long Axis, in (mm)...	0,43 (11,0)	0,43 (10,9)	0,43 (10,9)	0,41 (10,5)	0,42 (10,7)	0,43 (10,8)	0,41 (10,4)	0,43 (11,0)	0,40 (10,1)			0,43 (11,00)
Average Casing Hole Diameter, in (mm).....	0,42 (10,65)	0,43 (10,85)	0,42 (10,55)	0,41 (10,40)	0,41 (10,45)	0,42 (10,65)	0,41 (10,30)	0,43 (10,95)	0,40 (10,10)			0,42 (10,78)
Total Depth, in (mm).....	62,8 (1595,6)	LOST	LOST	66,6 (1690,6)	59,1 (1500,6)	58,3 (1480,6)	53,0 (1345,6)	50,6 (1285,6)	64,6 (1641,6)			60,9 (1547,75)
Burr Height, in (mm).....	0,08 (2,0)	0,07 (1,8)	0,06 (1,5)	0,08 (2,0)	0,04 (1,1)	0,05 (1,3)	0,06 (1,5)	0,09 (2,2)	0,06 (1,6)			0,07 (1,84)

Remarks The gun can be used in gas wells. Penetration normalized to 5000 psi by method of SPE 27424 (approx. 3,8% / 1000psi) = 63,8 " (1620 mm)

Witnessed by: K. Poliakov WITNESSING INFORMATION

Optionally Witnessed Activities: Target Pouring Briquette Preparation Briquette Testing Burr Height Measurements

I certify that these tests were made according to the procedures as outlined in API 19B: Recommended Practice for Evaluation of Well Perforators, Second Edition, September 2006. All of the equipment used in these tests, such as the guns, jet charges, detonator cord, etc., was standard equipment with our company for the use in the gun being tested and was not changed in any manner for the test. Furthermore, the equipment was chosen at random from stock and therefore will be substantially the same as the equipment that would be furnished to perforate a well for any operator. API neither endorses these tests nor recommends the use of the perforator system describes.

Penetration data recorded in API RP 19B Section 1 may not directly correlate to penetration downhole

X CERTIFIED BY A. Yakuba Director for Project Management October 16, 2015 BVT, CJSC 41 Rabochaya St., Samara, 443041, Russian Federation
 (Company Official) (Title) (Date) (Company) (Address)

Name of test as it should appear on website: PKO114-AT / ZPK114-AT-M-04

Name of test as it appear on application and application date: PKO114-AT / ZPK114-AT-M-04 August 19, 2015